

Pauling's Fifth Rule

- ❖ The number of essentially different kinds of constituents in a crystal tends to be small, or
- ❖ the number of types of interstitial sites present within a periodically regular packing of anions tends to be small